

LX

Polyester Mesh (Monofilament : Partially-fused type)

Nittoku

Fabric No.	Type of weave	Mesh count	Diameter	Mesh opening	Opening area	Thickness	Ink volume	Available width			
								cm	115	135	165
		/inch	μm	μm	%	μm	cm3/m2	inch	45	53	65
60SS	PW	60	55	368	76	93	70		●	●	●
70SS	PW	70	55	308	72	92	66		●	●	●
80SS	PW	80	55	263	68	92	63		●	●	●
100SS	PW	100	48	206	66	81	53		●	●	●
100S	PW	100	55	199	61	90	55		●	●	●
120S	PW	120	48	164	60	71	42		●	●	●
135S	PW	135	48	140	55	78	43				●
150S	PW	150	48	121	51	78	40				●
180S	PW	180	48	93	44	77	33				●

LH

Polyester Mesh (Monofilament x Multifilament : Completely-fused type)

Nittoku

Fabric No.	Type of weave	Mesh count	Diameter	Mesh opening	Opening area	Thickness	Ink volume	Available width	
								cm	135
		/inch	μm	μm	%	μm	cm3/m2	inch	53
24T	PW	24	55 × 65	998	89	72	64		●
30T	PW	30	55 × 65	787	86	75	65		●

■ Available width (status of production availability)

- =Regular product (Products are manufactured based on past records, but this does not guarantee future manufacturing conditions.)

Blank=Ordered product (Some products may be available. Please feel free to contact us.)

■ Calculations of the mesh opening, opening area, and ink volume are based on the number of mesh and the diameter.

■ Type of weave indicates PW=plain weaving and TW=twill weaving.

■ The specifications are standard values and not guaranteed values.

■ Please note that these specifications are subject to change without prior notice for improvements.